



The Shepherd Color Company
We Brighten Lives

TECHNICAL DATA SHEET

TDS #325
Revision 1
Page 1 of 1

BLACK 10C931

C.I. Pigment Black 26
CAS # 68186-94-7*

DESCRIPTION: A jet-black powder produced by high temperature calcination. This pigment has good UV and visible opacity, is chemically inert, heat resistant, and stable to ultraviolet light. It is non-bleeding and non-migratory. It has exceptional durability and hiding power, and is generally used in applications where the absence of chromium is desired and resistance to heat, light, and weather are needed. It is compatible with most resin systems and polymers, and is non-warping. Typical applications (non inclusive) are high-temperature liquid and powder coatings, inks, dispersions, plastics, and other applications where equivalent pigment chemistry is used.

COMPOSITION: Copper, Iron and Manganese

Physical/Chemical Property	Typical Value	Units	Test Method+
Specific Gravity	5.1	n/a	SCTM 312
Loose Packing Density	6.3 0.75	lbs./gal kg/L	SCTM 194
Surface Area (BET)	12	m ² /g	SCTM 153
Percent Moisture	0.4	wt. %	SCTM 248
Mean Particle Size	1.6	microns	SCTM 183
Conductivity	253	μS/cm	SCTM 142
Oil Absorption	11	parts oil/100 parts pigment	SCTM134
pH	6.7	n/a	SCTM 101
Residue 325 Mesh	0.2	wt. %	SCTM 135
Heat Stability	>1000 >540	°F °C	Observed

+SCTM refers to Shepherd Color Testing Method

Issued by: Brian Schwer-Technical Support Lab Manager Issue Date: July 21, 2009

This document is not subject to the requirements of the Shepherd Color internal control procedure. This information provided hereon is based on tests believed to be reliable. However, this data is not guaranteed and no warranty, either expressed or implied is made concerning the use of this information or the use of the product described, whether or not known to The Shepherd Color Company.